



**BLUE LABEL CO.,LTD.**

48/58 Moo.1 Ekachai Road, Khok-Krabue, Amphur Muang, Samutsakhon, 74000 Thailand  
Tel : +66 3449 4774-5 Fax : +66 3449 4776 Website : www.bluelabelgroup.com

*Technical Data Sheet*

**RHINOZ – Innovation Special Products**

# **RHINOZ<sup>®</sup> RF-102**

## **RHINOZ Acrylic Skim**

### **FEATURES**

- Easy to apply by trowel
- High bonding strength
- Perfectly smooth finish
- High flexible
- Good weather resistance
- No crack and low smell
- Multi-layer coated without cracking
- Safe and environmentally friendly

### **DESCRIPTIONS**

It is a skim smoothing rendering paste and ready to use formula for repairing surface defects in concrete or render. A smooth surface is obtained by eliminating blemishes such as grooves, seams, fine cracks and rock pockets. It is suitable for fiber cement, fiber concrete, gypsum concrete, especially for wall and ceiling with good adhesion and weathering resistance, perfectly smooth finish, high flexible, no crack, no chalk and can be sanded and paintable

### **APPLICATION**

1. Surface must be clean, free of dust, oil, grease and other contaminates
2. Spray small amount of water on surface or use damp cloth wipe off surface before apply RHINOZ Acrylic Skim
3. Apply by stainless or steel trowel, apply one or several coats, can be recoated after 1-2 hours
4. It can be sanded after 16-24 hours and painting can be done after 24 hours
5. Clean tools and equipment with detergent and water

### **PACKING SIZE**

5 kg.      25 kg.

### **STORAGE**

Store in a dry place with shelf life 1 year in the original unopened packing

### **TECHNICAL DATA**

Base	:	Acrylic polymer	
Appearance	:	Viscous paste	
Colour	:	See colour chart	
pH	:	8.0 - 10.0	
Density	:	1.5 - 1.6 g/cm <sup>3</sup>	
Surface dry	:	15 - 20 minutes	( Depending on ambient conditions and thickness )
Recoating dry	:	1 - 2 hours	( Depending on ambient conditions and thickness )
Sand able	:	16 - 24 hours	( Depending on ambient conditions and thickness )
Cure time	:	7 days	( Depending on ambient conditions and thickness )
Bond strength	:	>1.5 N/mm <sup>2</sup>	( ASTM D4541 )
Coverage	:	1.5 kg./m <sup>2</sup> /1 mm.	